

Alkoxylates

Promoting superior performance

Product data summary

Name	Functionality	Hydroxyl number (mg KOH/g)	Molecular weight (g/mol)	Viscosity (mPas, 23 °C)	Recommended applications		
					General	Radcure	Poly- urethane
Polyol R2395	2	395	276	350		•	•
Polyol R2490	2	490	220	170		•	•
Polyol 3165	3	165	1,014	350	•		•
Polyol 3380	3	380	444	360	•	•	
Polyol 3610	3	610	275	700			•
Polyol 3611	3	611	275	700			•
Polyol 3940	3	940	179	4,000			•
Polyol 3990	3	990	170	4,500	•		•
Polyol R3215	3	215	795	340	•	•	
Polyol R3430	3	430	398	400		•	
Polyol R3530	3	530	308	2,000	•	•	•
Polyol R3540	3	540	311	550		•	
Polyol R3600	3	600	275	700		•	
Polyol 4290	4	290	797	450	•		
Polyol 4360	4	360	629	1,300			•
Polyol 4525	4	525	426	2,600			•
Polyol 4640	4	640	355	1,100			•
Polyol 4800	4	800	282	2,200			•
Polyol R4630	4	630	350	1,500		•	
Polyol R4631	4	631	356	1,500		•	
Polyol R6405	6	405	827	1,900	•	•	•