


# Boltorn™ H20

## Development product



### Description

- Boltorn™ H20 is only intended as starting material for development of dendritic derivatives.
- Boltorn™ H20 is a dendritic polymer with theoretically 16 primary hydroxyl groups.
- Boltorn™ H20 has a highly branched polyester structure.
- Boltorn™ H20 is an amorphous solid at room temperature.
- Boltorn™ H20 is delivered in pellets
- Boltorn™ H20 is produced in limited quantities and only against order.

### Applications

- Coatings
- Plastics
- The dendritic structure offers unique possibilities by combining excellent reactivity with low viscosity and enhanced mechanical properties.
- Boltorn™ H20 is an excellent building block for designing novel products.
- Its ability to promote dense branching of a polymer backbone without crosslinking is highly appreciated in many applications.

### Delivery forms

- Plastic containers 20 kg, 360kg/pallet

### Storage

- Boltorn™ H20 is hygroscopic and should be handled to prevent moisture absorption.

### Sales specification

Hydroxyl number, mg KOH/g <sup>1</sup>	490-530
Acid number, mg KOH/g <sup>2</sup>	Max. 9

### Typical properties

Molecular weight, M <sub>w</sub> , g/mole <sup>3</sup>	2100
Polydispersity, M <sub>w</sub> /M <sub>n</sub> <sup>3</sup>	1.3
Viscosity (110 °C, 30 s <sup>-1</sup> ), Pas <sup>4</sup>	7
Glass transition temperature, T <sub>g</sub> , °C <sup>5</sup>	30

#### Analytical Method

<sup>1</sup> PO 100-9, <sup>2</sup> PO 110-4, <sup>3</sup> PO 137-1, <sup>4</sup> PO 120-3,

<sup>5</sup> DMA Tan δ peak (Netzch DMA 242 3-point bending 1 Hz 3 °C/min)

Analytical methods are available on request

HS no.: 3907 99

CAS no.: 326794-48-3

Valid from: December 20, 2010

Supersedes: January 1, 2003

Approved: 18 Feb 2011

Issue: 3

Approved by: PERSTORP\septpnsa